D-EUROGRES

GRANITE TILE

GRANITE TILES brochure

0.jpg

Digital Polish

Size Available : 60 x 60 cm

Sandrino

Saverio

Fontana Marble

Bianco Ibiza

Jade

Digital Polish

Size Available : 60 x 60 cm & 60 x 120 cm

Crema Cenia

Botticino Marble

Trigato Orientale

Arenisca Madera

Mistral White

Venito Bianco

Valerio

Serafino

Maroon Emperador

Double Loading

Size Available : 60 x 60 cm & 80 x 80 cm | 80 x 80 cm (*)


Carara White

Alaska

Whiskey

Manhattan Gold*

Manhattan Silver*

Glazed Porcelain

Size Available : 60 x 60 cm

Megalito Black

Yura Cream

Nordik Grey

Yura Grey

Martino Wood

Massimo Wood

Marmaro

Size Available : 60 x 60 cm & 80 x 80 cm | 80 x 80 cm (*)

Grand Royal Marble



Lotus White

Mahony Royal



Creme Marble

Norte



White Fuji*

2.jpg

TECHNICAL STANDARD

Porcelain Tiles

Porcelain Tiles are produced according to the specification of MS ISO 13006 (Annex G)

Description	MS ISO 13006 (Annex G)
Length and Width	±0.6%
Thickness	±5.0%
Straightness of Sides Rectangularity	±0.5% ±0.6%
Surface Flatness - Centre Curvature - Edge Curvature - Warpage	±0.5% ±0.5% ±0.5%
Surface Quality	Min 95% defect free*
Water Absorption	≤ 0.5%
Breaking Strength - Thickness ≥ 7.5 mm	Min 1300N
Modulus of Rupture (MOR)	Min 35N/mm²
Abrasive Resistance (PEI) for glazed porcelain tiles Resistance to deep abrasion for unglazed tiles (Volume removed)	Dependent on product type Max 175mm³
Frost Resistance	Required (where frost exist)
Resistance to acids and alkalis (except hydrofluoric acids and its compound) Resistance to household chemicals and swimming pool water cleansers (except to cleansing agents containing hydrofluoric acids and its compound)	Min Class B Min Class B
Stain Resistance - Glazed Tiles Polished / Unglazed Tiles	Min Class 3 Not Required**
Slip Resistance	Indicated in the catalogue

* A minimum of 95% of the tiles be free from visible defects that would impair the appearance of a major area of tiles.
** Semi polished / polished porcelain tiles are more susceptible to staining because dirt gets trapped in the opened surface pores. For this reason, particular care must be taken when using a contrasting grout colour or when selecting a light patterned tile. Sealants or other pre-surface treatments can prevent this problem as long as routine re-application of the protective treatment is maintained.

SANDIMAS
GRANITE & SANITARY

www.sandimas.co.id

Sandimas @Sandimas_cs

3.jpg